

## Everlast® Composite Siding – Board & Batten

Everlast® Composite Siding panels are manufactured to the following specifications.

### Physical Data

Panel Thickness: 0.325" ( $\pm 0.015$ " )  
Panel Projection: 3/4"  
Width: 12 1/2"  $\pm 1/16$ "  
Exposure/Reveal: 11"  
Length: 12'  
Weight: 15.7 lbs/plank  
Packaging: 6 planks/bundle  
Color: Uniformity is spectrophotometrically controlled.  
Texture: Embossed with a rough cut cedar finish  
Gloss: Uniform low gloss maintained with a 75° gloss meter

### Product Test Data

Heat Shrinkage: 0.1% at 160°F  
Static Wind load Test Pressure: 80.3 psf. (180 mph) screws  
Squareness:  $< 1/16$ " of square  
Length: Within  $- 1/8$ " of specification  
Warp/Camber:  $< 1/16$ "  
Coefficient of Linear Expansion (in/in/°F):  $8.38 \times 10^{-6}$   
Weathering and Flexural: 104.4% Strength Retention  
Freeze Thaw and Flexural: 94.1% Strength Retention  
Water Absorption per ASTM D-570:  $< 2.0\%$  Long Term (3 weeks)

### Fire Resistance

#### ASTM E84:

Flame Spread Index: 75  
Smoke Developed Index:  $> 450$

#### ASTM D635:

Classified CC1  
Rate of burn: No Self Sustained Burn

#### ASTM D-1929:

Self-Ignition/Flash Ignition Temperature: 430°C/400°C

### Relevant Codes and Regulations Compliance

Code Compliance Research Report CCRR-0201 Revision 10/16/19  
DBPR Florida Code #FL22980-R1 Chelsea Building Products



### Colors

- Blue Spruce
- Cabernet Red
- Chestnut
- Flagstone
- Misty Taupe
- Natural White
- Saddle Wood
- Sand Dune
- Seaside Gray
- Storm Grey

All colors feature capping resins, a UV-Stable acrylic polymer for exceptional color retention.

